


BLACK BEAN

The heartwood ranges from dark brown to chocolate shades deepening almost to black; sometimes streaked with lighter coloured bands. Grain is usually straight but can be wavy or interlocked resulting in deep, decorative appearance.

Hardness: (Janka) Rating: 7.5

Density: 770 (kg/m³dry)

Application: Flooring, Panelling, Furniture, Joinery, Veneer, Wood Turning, Boat Building, Musical Instruments




QUEENSLAND SILVER ASH

The heartwood ranges from silver-white to pale yellow shades. Slight grain deviation may occur associated with bumps on the log surface. There is no pronounced figure but a characteristic of the species is its long straight vessel lines on longitudinal surfaces.

Hardness (Janka) Rating: 5

Density: 640-675 (kg/m³dry)

Application: Flooring, Panelling, Furniture, Joinery, Veneer, Wood Turning, Musical Instruments




BRIAR OAK

Briar Oak is a light golden brown/bronze colour and displays tight medullary rays when quarter sawn. It is similar to Northern Silky Oak in appearance but has a deeper bronze colour with distinct highlights. Briar Oak works well with both machine tools and hand tools. This is a premium product ideal for solid timber furniture market and high-end interiors market such as flooring.

Hardness: (Janka) Rating: 6

Density: 675 (kg/m³dry)

Application: Flooring, Panelling, Cladding, Furniture, Joinery, Veneer, Wood Turning, Musical Instruments




RED TULIP OAK

Red Tulip Oak is a deep brown colour with a hint of red. The grain is moderately open and the fibers are long. This timber is ideally suited to the premium flooring and paneling market and will be the king of hardwood flooring.

Hardness: (Janka) Rating: 9

Density: 800/925 (kg/m³dry)

Application: Flooring, Panelling, Furniture, Joinery, Veneer, Wood Turning, , Musical Instruments




NORTHERN SILKY OAK

Northern Silky Oak has a beautifully golden colour with brown tones and, when quarter sawn, very prominent medullary rays. The timber is of medium density and medium hardness. Northern Silky Oak works well with machining and hand tools.

Hardness: (Janka) Rating: 6

Density: 560 kg/m³dry)

Application: Panelling, Cladding, Furniture, Joinery, Veneer, Wood Turning, Musical Instruments




SILVER QUANDONG

The heartwood is generally white to cream white. In some cases it can have greyish or light brownish tones. Porous and open grained. It has a hardness greater than Tasmanian Oak and is comparable to eucalypts, making it suitable for joinery and furniture.

Hardness: (Janka) Rating: 2.6

Density: 495 (kg/m³dry)

Application: Panelling, Cladding, Furniture, Joinery, Veneer, Wood Turning, Boat Building, Musical Instruments




QUEENSLAND MAPLE

Queensland Maple has an orange/red colour with brown tones. The timber is close-grained, of medium density and medium hardness. Queensland Maple works well with machining and hand tools.

Hardness: (Janka) Rating: 4.7

Density: 575 kg/m³dry)

Application: Panelling, Cladding, Furniture, Joinery, Veneer, Wood Turning, Boat Building, Musical Instruments



RED SILKWOOD

The heartwood is generally pink to red-brown but varies between species. Grain wood is straight to interlocked with a moderately fine texture

Hardness: (Janka) Rating: 6

Density: 540 (kg/m³dry)

Application: Panelling, Furniture, Joinery, Veneer, Wood Turning, , Musical Instruments