

AMERICAN BLACK WALNUT

Juglans Nigra



www.brittontimbers.com.au



Description

The sapwood is creamy white, heartwood is light brown to dark chocolate brown, occasionally with a purplish cast and darker streaks.

Walnut can be supplied steamed, to darken sapwood or left unsteamed. Generally straight grained, but sometimes has attractive wavy or curly grain.

Also known as Black Walnut, American Walnut.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✗ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	609	Hardness (Janka) (kN)	5	Resistance to Split in Nailing	Good
Specific Gravity	0.55	Finish	Excellent	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	100	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	11	Durable	No	Growing Region	North America
Radial Shrinkage %	3	Sapwood Lyctid Susceptible	Yes	Availability	Widely
Tangential Shrinkage %	4	Machining	Excellent		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522



The mark of
responsible forestry