




AMERICAN RED OAK

Quercus Rubra



www.brittontimbers.com.au



Description

The sapwood is white to light brown and the heartwood is a pinkish reddish brown. The wood appears similar to white oak, but with slightly less pronounced figure.

The wood is mostly straight grained, with a coarse texture.

Also known as Northern Red Oak, Southern Red Oak.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✗ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	705	Hardness (Janka) (kN)	6	Resistance to Split in Nailing	Good
Specific Gravity	0.64	Finish	Excellent	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	99	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	12	Durable	No	Growing Region	North America
Radial Shrinkage %	3	Sapwood Lyctid Susceptible	Yes	Availability	Widely
Tangential Shrinkage %	5	Machining	Excellent		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522



FSC® C113479

The mark of responsible forestry