



Description

Heartwood pale brown, but northern material may sometimes display a slight pinkish tinge. Sapwood distinctively paler.

Texture medium and even. Grain usually straight. Gum veins are common.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	900	Hardness (Janka) (kN)	9	Resistance to Split in Nailing	Good
Specific Gravity	0.9	Finish	Good	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	144	Stability	Good	Gluing	Poor
Modulus of Elasticity (GPa dry)	19	Durable	Yes	Growing Region	NSW & QLD
Radial Shrinkage %	4	Sapwood Lyctid Susceptible	No	Availability	Widely
Tangential Shrinkage %	7	Machining	Good		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522