



## Description

A large, fast growing plantation hardwood. Heartwood pink to pale red. Sapwood not always clearly differentiated.

Texture moderately coarse but even. Grain straight. Excellent for mill work.

Available in long lengths.

*Also known as Red Grandis.*

## Suitability

- ✗ Boating
- ✓ Cabinet Door
- ✗ Decking & Cladding
- ✗ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

## TECHNICAL INFORMATION

Density (kg/m <sup>3</sup> dry)	550	Hardness (Janka) (kN)	5.5	Resistance to Split in Nailing	Good
Specific Gravity	0.60	Finish	Good	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	87	Stability	Fair	Gluing	Good
Modulus of Elasticity (GPa dry)	12	Durable	Yes	Growing Region	Uruguay
Radial Shrinkage %	4	Sapwood Lyctid Susceptible	No	Availability	Widely
Tangential Shrinkage %	7	Machining	Good		

### New South Wales

116-118 Jemma Rd  
Prestons NSW 2170

☎ 02 8783 9900

### Victoria

25 Gaine Rd  
Dandenong VIC 3175

☎ 03 8769 7111

### Queensland

29 Sodium St  
Narangba QLD 4504

☎ 07 3888 3351

### Tasmania

3 Brittons Rd  
Smithton TAS 7330

☎ 03 6452 2522

