

IRONBARK GREY

Eucalyptus Paniculata



www.brittontimbers.com.au



Description

Heartwood colour varies from pale brown to dark chocolate brown and also dark red.

Texture moderately coarse and even. Grain usually interlocked.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	1120	Hardness (Janka) (kN)	14	Resistance to Split in Nailing	Fair
Specific Gravity	1.1	Finish	Fair	Resistance to Split in Screwing	Fair
Modulus of Rupture (MPa dry)	181	Stability	Fair	Gluing	Poor
Modulus of Elasticity (GPa dry)	24	Durable	Yes	Growing Region	NSW & QLD
Radial Shrinkage %	4.5	Sapwood Lyctid Susceptible	No	Availability	Limited
Tangential Shrinkage %	8	Machining	Fair		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522



PEFC/21-31-233



AFS/01-31-233