



Description

Heartwood is creamy white to straw coloured.

The grain is almost straight, the texture fine and even and of plain appearance.

Jelutong is mainly used for pattern making.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✗ Decking & Cladding
- ✗ Flooring & Staircase
- ✗ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

| | | | | | |
|---------------------------------|------|----------------------------|-----------|---------------------------------|--------------|
| Density (kg/m ³ dry) | 400 | Hardness (Janka) (kN) | 2 | Resistance to Split in Nailing | Excellent |
| Specific Gravity | 0.46 | Finish | Excellent | Resistance to Split in Screwing | Excellent |
| Modulus of Rupture (MPa dry) | 50 | Stability | Excellent | Gluing | Good |
| Modulus of Elasticity (GPa dry) | 8 | Durable | No | Growing Region | Asia Pacific |
| Radial Shrinkage % | 1 | Sapwood Lyctid Susceptible | Yes | Availability | Available |
| Tangential Shrinkage % | 2 | Machining | Excellent | | |

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522