



Description

Heartwood is reddish brown, paler in colour than Jarrah when fresh, but maturing to a more uniform brown.

The grain is interlocked with some wavy grain, the texture is even and moderately coarse.

Also known as Western Australian Karri.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	900	Hardness (Janka) (kN)	9	Resistance to Split in Nailing	Fair
Specific Gravity	0.88	Finish	Good	Resistance to Split in Screwing	Fair
Modulus of Rupture (MPa dry)	132	Stability	Good	Gluing	Fair
Modulus of Elasticity (GPa dry)	19	Durable	Yes	Growing Region	WA
Radial Shrinkage %	4.5	Sapwood Lyctid Susceptible	No	Availability	Widely
Tangential Shrinkage %	10	Machining	Fair		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522