

RIVER RED GUM

Eucalyptus Camaldulensis, Eucalyptus Rostrata



www.brittontimbers.com.au



Description

The heartwood varies according to location in age, from pink to dark red.

The grain is interlocked and frequently wavy which produces a fiddleback figure when quarter cut. The texture is close and even.

The wood is resinous with frequent gum pockets. The surface is often distinctly mottled.

Also known as Murray Red Gum.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	900	Hardness (Janka) (kN)	10	Resistance to Split in Nailing	Fair
Specific Gravity	0.9	Finish	Good	Resistance to Split in Screwing	Fair
Modulus of Rupture (MPa dry)	101	Stability	Good	Gluing	Fair
Modulus of Elasticity (GPa dry)	11	Durable	Yes	Growing Region	VIC
Radial Shrinkage %	2.5	Sapwood Lyctid Susceptible	Yes	Availability	Available
Tangential Shrinkage %	4	Machining	Fair		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522