

ROSE GUM

Eucalyptus Grandis



www.brittontimbers.com.au



Description

Heartwood pink to pale red brown. Sapwood not always clearly differentiated.

Texture moderately coarse but even. Grain straight.

Also known as Flooded Gum.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	700	Hardness (Janka) (kN)	8	Resistance to Split in Nailing	Good
Specific Gravity	0.7	Finish	Good	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	122	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	17	Durable	Yes	Growing Region	NSW & QLD
Radial Shrinkage %	4	Sapwood Lyctid Susceptible	No	Availability	Available
Tangential Shrinkage %	7	Machining	Good		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522



PEFC™
PEFC/21-31-233



AFS/01-31-233