



Description

Heartwood can be either golden brown or a dark blood red. Sapwood pale yellow.

Texture medium. Grain variable.

The freshly cut wood has a fragrant odour often highly figured.

Also known as New Guinea Rosewood, Solomon Islands Rosewood.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	650	Hardness (Janka) (kN)	5	Resistance to Split in Nailing	Good
Specific Gravity	0.65	Finish	Excellent	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	95	Stability	Excellent	Gluing	Good
Modulus of Elasticity (GPa dry)	12	Durable	Yes	Growing Region	Asia Pacific
Radial Shrinkage %	1	Sapwood Lyctid Susceptible	No	Availability	Available
Tangential Shrinkage %	2	Machining	Excellent		

New South Wales

116-118 Jedda Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522