



## Description

Heartwood is pink when freshly cut to red brown or purple brown. Sapwood grey pink or cream.

Interlocked grain producing a narrow and uniformly distributed stripe on the radial surface. Texture fine and even.

The wood has a slight cedar like odour when freshly cut.

*Also known as Sapeli, Sapelli, Sapelle.*

## Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✗ Decking & Cladding
- ✗ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

## TECHNICAL INFORMATION

Density (kg/m <sup>3</sup> dry)	690	Hardness (Janka) (kN)	7	Resistance to Split in Nailing	Good
Specific Gravity	0.62	Finish	Excellent	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	110	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	12	Durable	Yes	Growing Region	Africa
Radial Shrinkage %	2	Sapwood Lyctid Susceptible	Yes	Availability	Widely
Tangential Shrinkage %	4	Machining	Good		

### New South Wales

116-118 Jemma Rd  
Prestons NSW 2170

☎ 02 8783 9900

### Victoria

25 Gaine Rd  
Dandenong VIC 3175

☎ 03 8769 7111

### Queensland

29 Sodium St  
Narangba QLD 4504

☎ 07 3888 3351

### Tasmania

3 Brittons Rd  
Smithton TAS 7330

☎ 03 6452 2522

