


SILVERTOP ASH

Eucalyptus Sieberi



www.brittontimbers.com.au



Description

Straight-grained timber that often features gum veins, ambrosia, growth rings and pencil steaks which add individuality to any project.

The colour palette ranges from pale to medium browns with a hint of pink. Provides good fire resistance.

Also known as Coast Ash, Ironbark, Black Ash.

Suitability

- ✗ Boating
- ✗ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	850	Hardness (Janka) (kN)	9.5	Resistance to Split in Nailing	Fair
Specific Gravity	0.68	Finish	Good	Resistance to Split in Screwing	Fair
Modulus of Rupture (MPa dry)	136	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	17	Durable	Yes	Growing Region	VIC & NSW
Radial Shrinkage %	5	Sapwood Lyctid Susceptible	No	Availability	Available
Tangential Shrinkage %	10.6	Machining	Good		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522



PEFC
PEFC/21-31-233



Australian Forestry Standard
AFS/01-31-233