



## Description

Heartwood golden brown, often with dark markings. Sapwood pale yellow and easily distinguished. The wood contains an oleo-resin, which gives it a greasy feel and a distinctive odour to freshly cut material.

Texture uneven, alternatively smooth and coarse because of the wood's ring-porous nature. Grain usually straight. Freshly cut wood can be very variable in colour, with blotches and streaks, but prolonged exposure to light modifies the more extreme variations.

*Also known as Burmese Teak.*

## Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

## TECHNICAL INFORMATION

Density (kg/m <sup>3</sup> dry)	670	Hardness (Janka) (kN)	4.5	Resistance to Split in Nailing	Good
Specific Gravity	0.67	Finish	Excellent	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	106	Stability	Excellent	Gluing	Fair
Modulus of Elasticity (GPa dry)	10	Durable	Yes	Growing Region	Asia Pacific
Radial Shrinkage %	1.5	Sapwood Lyctid Susceptible	No	Availability	Available
Tangential Shrinkage %	2.5	Machining	Good		

### New South Wales

116-118 Jemma Rd  
Prestons NSW 2170

☎ 02 8783 9900

### Victoria

25 Gaine Rd  
Dandenong VIC 3175

☎ 03 8769 7111

### Queensland

29 Sodium St  
Narangba QLD 4504

☎ 07 3888 3351

### Tasmania

3 Brittons Rd  
Smithton TAS 7330

☎ 03 6452 2522