

# VICTORIAN ASH

*Eucalyptus Regnans, Eucalyptus Delegatensis*



www.brittontimbers.com.au



## Description

Heartwood pale pink or pale straw. Sapwood not always clearly differentiated.

Texture rather coarse. Grain straight. Growth rings conspicuous. Gum veins common.

Also known as Mountain Ash, Alpine Ash.

## Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✗ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

## TECHNICAL INFORMATION

Density (kg/m <sup>3</sup> dry)	680	Hardness (Janka) (kN)	5	Resistance to Split in Nailing	Good
Specific Gravity	0.7	Finish	Good	Resistance to Split in Screwing	Good
Modulus of Rupture (MPa dry)	110	Stability	Good	Gluing	Good
Modulus of Elasticity (GPa dry)	15	Durable	No	Growing Region	VIC
Radial Shrinkage %	5	Sapwood Lyctid Susceptible	Yes	Availability	Widely
Tangential Shrinkage %	8.5	Machining	Good		

### New South Wales

116-118 Jemma Rd  
Prestons NSW 2170

☎ 02 8783 9900

### Victoria

25 Gaine Rd  
Dandenong VIC 3175

☎ 03 8769 7111

### Queensland

29 Sodium St  
Narangba QLD 4504

☎ 07 3888 3351

### Tasmania

3 Brittons Rd  
Smithton TAS 7330

☎ 03 6452 2522



PEFC/21-31-233



AFS/01-31-233