



Description

The clearly defined heartwood is dark brown, with very close, fine, almost black veins.

The closely spaced whitish bands parenchyma give the wood a most attractive appearance.

It is fairly straight grained with a coarse texture.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✗ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

Density (kg/m ³ dry)	910	Hardness (Janka) (kN)	10	Resistance to Split in Nailing	Fair
Specific Gravity	0.74	Finish	Good	Resistance to Split in Screwing	Fair
Modulus of Rupture (MPa dry)	152	Stability	Good	Gluing	Fair
Modulus of Elasticity (GPa dry)	16	Durable	Yes	Growing Region	Africa
Radial Shrinkage %	3	Sapwood Lyctid Susceptible	No	Availability	Available
Tangential Shrinkage %	6	Machining	Good		

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522