

BLACKBUTT DECKING

Eucalyptus Pilularis

Blackbutt is a coarse-textured, strain-grained timber typical of the harsh Australian coastal climate in which it thrives.

It's hard and tough but relatively easily worked - qualities that have made it a popular choice for decking.

Blackbutt is honey blonde coloured and its sapwood is resistant to borers.

For decking projects where good-looks, durability and stability are required, Britton Timbers Blackbutt is the natural choice.

Blackbutt provides good fire resistance, and is one of seven hardwood species that was found suitable for construction in bushfire prone areas.

Britton Timbers supplies Blackbutt decking Australia-wide from our Melbourne, Sydney and Brisbane distribution centres and overseas markets through Britton Timbers International.

Sizes: 86mm x 19mm Pencil Round Four Corners
130mm x 19mm Pencil Round Four Corners

BAL: Bushfire Attack Level 12.5, 19 & 29
All AS 3959 Required Applications



TECHNICAL INFORMATION

Density (kg/m ³ dry)	900	Tangential Shrinkage %	7	Machining	Good
Specific Gravity	0.9	Hardness (Janka) (kN)	9	Resistance to Split in Nailing	Good
Modulus of Rupture (MPa dry)	144	Finish	Good	Resistance to Split in Screwing	Good
Modulus of Elasticity (GPa dry)	19	Stability	Good	Gluing	Poor
Radial Shrinkage %	4	Sapwood Lyctid Susceptible	No	Growing Region	NSW & QLD
				Availability	Widely