


Accoya

Radiata Pine

Accoya® is wood is chemical free modified timber using acetylation, which enables it to resist rot and defy the elements. Guaranteed for 50 years above ground and 25 years in ground. From joinery for the home to bridges submerged in water, Accoya® long life wood is a leading material that stands up to every application challenge.

Application Suitability

Decking & Cladding • Joinery • Boating • Furniture • Cabinetry



| | |
|---------------------------------|------|
| Density | 515 |
| Specific Gravity | 0.51 |
| Modulus of Rupture (Mpa Dry) | 90 |
| Modulus of Elasticity (Gpa Dry) | 9 |
| Radial Shrinkage | 0.4% |
| Tangential Shrinkage | 0.8% |

| | |
|----------------------------|-----------|
| Hardness (janka) (kN) | 4.1 |
| Finish | Excellent |
| Gluing | Good |
| Machining | Excellent |
| Sapwood Lyctid susceptible | No |

| | |
|---------------------------|---------|
| Stability | Good |
| Durability | Durable |
| Screwing Split Resistance | Good |
| Nailing Split Resistance | Fair |
| Growing region | Europe |
| Availability | Widely |

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322



brittontimbers.com.au

