


American Ash

Franxinus Americana

Similar in appearance to European ash. The sapwood is light coloured to nearly white and the heartwood varies from greyish brown to pale yellow streaked with brown. The wood is generally straight-grained with a coarse, uniform texture. Also known as Northern Ash, Southern Ash, White Ash.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Boating



Density	675
Specific Gravity	0.60
Modulus of Rupture (Mpa Dry)	104
Modulus of Elasticity (Gpa Dry)	12
Radial Shrinkage	4%
Tangential Shrinkage	7%

Hardness (janka) (kN)	6.0
Finish	Excellent
Gluing	Good
Machining	Good
Sapwood Lyctid susceptible	Yes

Stability	Good
Durability	Non Durable
Screwing Split Resistance	Good
Nailing Split Resistance	Good
Growing region	North America
Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322



brittontimbers.com.au

