



American Black Walnut

Juglans Nigra

The sapwood is creamy white, heartwood is light brown to dark chocolate brown, occasionally with a purplish cast and darker streaks. Walnut can be supplied steamed, to darken sapwood or left unsteamed. Generally straight grained, but sometimes has attractive wavy or curly grain. Also known as Black Walnut, American Walnut.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Boating



Density	609
Specific Gravity	0.55
Modulus of Rupture (Mpa Dry)	100
Modulus of Elasticity (Gpa Dry)	11
Radial Shrinkage	3%
Tangential Shrinkage	4%

Hardness (janka) (kN)	5.0
Finish	Excellent
Gluing	Good
Machining	Excellent
Sapwood Lyctid susceptible	Yes

Stability	Good
Durability	Non Durable
Screwing Split Resistance	Good
Nailing Split Resistance	Good
Growing region	North America
Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170