

Australian Chestnut

Eucalyptus Obliqua, Eucalyptus Sieberi, Eucalyptus Fastigata

Flooring is characterised by subtle colour variations from mellow straw brown to light chocolates. Durable eucalypts are blended to provide a sophisticated, natural beauty to any interior. Also known as Southern Blackbutt, Chestnut.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring



Density	800	Hardness (janka) (kN)	8.0	Stability	Good
Specific Gravity	0.80	Finish	Good	Durability	Durable
Modulus of Rupture (Mpa Dry)	118	Gluing	Good	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	15	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	3.5%	Sapwood Lyctid susceptible	No	Growing region	Australia
Tangential Shrinkage	6%			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

brittontimbers.com.au

