


# Australian Chestnut

*Eucalyptus Obliqua, Eucalyptus Sieberi, Eucalyptus Fastigata*

Flooring is characterised by subtle colour variations from mellow straw brown to light chocolates. Durable eucalypts are blended to provide a sophisticated, natural beauty to any interior. Also known as Southern Blackbutt, Chestnut.

## Application Suitability

Furniture • Cabinetry • Joinery • Flooring



Density	800
Specific Gravity	0.80
Modulus of Rupture (Mpa Dry)	118
Modulus of Elasticity (Gpa Dry)	15
Radial Shrinkage	3.5%
Tangential Shrinkage	6%

Hardness (janka) (kN)	8.0
Finish	Good
Gluing	Good
Machining	Good
Sapwood Lyctid susceptible	No

Stability	Good
Durability	Durable
Screwing Split Resistance	Good
Nailing Split Resistance	Good
Growing region	Australia
Availability	Widely

BT Tasmania (03) 6452 2522 3 Brittons Road Smithton, TAS 7330	BT New South Wales (02) 8783 9900 116-118 Jedda Road Prestons, NSW 2170	BT Queensland (07) 3888 3351 100 Potassium Street Narangba, QLD 4504	BT Victoria (03) 8769 7111 25 Gaine Road Dandenong, VIC	BT International +61 2 8783 9900 116-118 Jedda Road Prestons, NSW 2170	BT Veneer Products (03) 6435 1108 2 Elizabeth St Somerset TAS 7322
------------------------------------------------------------------------	----------------------------------------------------------------------------------	-------------------------------------------------------------------------------	------------------------------------------------------------------	---------------------------------------------------------------------------------	-----------------------------------------------------------------------------

