

# Black Bean

Branch 95

Heartwood ranges from Dark Brown to Chocolate shades deepening almost to black. Grain is usually straight but can be wavy or interlocked resulting in a deep, decorative appearance. The sapwood is white to yellow in colour with striated vessel lines prominent on longitudinal surfaces.

## Application Suitability

Flooring • Furniture • Joinery • Boating

Density	770	Hardness (janka) (kN)	7.5	Stability	Good
Modulus of Rupture (Mpa Dry)	115	Gluing	Difficult	Durability	1/1
Modulus of Elasticity (Gpa Dry)	15	Machining	Excellent	Screwing Split Resistance	Good
Radial Shrinkage	1.8	Sapwood Lyctid susceptible	Yes	Nailing Split Resistance	Good
Tangential Shrinkage	5.8			Growing region	QLD
				Availability	Widely

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
100 Potassium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170



[brittontimbers.com.au](http://brittontimbers.com.au)

