

Blackbutt

Eucalyptus Pilularis

Heartwood pale brown, but northern material may sometimes display a slight pinkish tinge. Sapwood distinctively paler. Texture medium and even. Grain usually straight. Gum veins are common.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding



Density	900
Specific Gravity	0.90
Modulus of Rupture (Mpa Dry)	144
Modulus of Elasticity (Gpa Dry)	19
Radial Shrinkage	4%
Tangential Shrinkage	7%

Hardness (janka) (kN)	9.0
BAL	29.0
Finish	Good
Gluing	Poor
Machining	Good
Sapwood Lyctid susceptible	No

Stability	Good
Durability	Durable
Screwing Split Resistance	Good
Nailing Split Resistance	Good
Growing region	Australia
Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322



brittontimbers.com.au

