

Blue Gum

Eucalyptus Saligna

Heartwood dark pink to red brown. Sapwood usually sufficiently paler to be readily distinguished. Texture moderately coarse and even. Grains straight or slightly interlocked. Gum veins common. Also known as Sydney Blue Gum.

Application Suitability

Decking & Cladding • Joinery • Flooring

Density	850	Hardness (janka) (kN)	9.0	Stability	Good
Specific Gravity	0.85	Finish	Good	Durability	Durable
Modulus of Rupture (Mpa Dry)	140	Gluing	Good	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	18	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	5%	Sapwood Lyctid susceptible	Yes	Growing region	Australia
Tangential Shrinkage	9%			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322

