

Briar Silky Oak

Branch 95

Golden brown/bronze colour and displays tight medullary rays when quarter sawn. It is similar to Northern Silky Oak in appearance but has a deeper bronze colour with distinct highlights and grain specific to Briar Oak. Briar Oak works well with both machine tools and hand tools.

Application Suitability

Flooring • Decking & Cladding • Furniture

Density	675	Hardness (janka) (kN)	4.5	Stability	Good
Modulus of Rupture (Mpa Dry)	77	Gluing	Great	Durability	3/4
Modulus of Elasticity (Gpa Dry)	10	Machining	Good	Screwing Split Resistance	Great
Radial Shrinkage	0.15	Sapwood Lyctid susceptible	No	Nailing Split Resistance	Great
Tangential Shrinkage	0.25			Growing region	QLD

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170



brittontimbers.com.au

