

Cambia Ash

Franxinus Americana

The Cambia thermal modification process uses high heat to improve its dimensional stability and decay resistance giving it a rich brown colour. Cambia products are more dimensionally stable and less prone to cup, warp and twist. Cambia does not contain any toxic chemicals.

Application Suitability

Flooring • Furniture • Cabinetry • Joinery • Decking & Cladding



Density	675
Specific Gravity	0.60
Modulus of Rupture (Mpa Dry)	104
Modulus of Elasticity (Gpa Dry)	12
Radial Shrinkage	4%
Tangential Shrinkage	7%

Hardness (janka) (kN)	6.0
Finish	Excellent
Gluing	Good
Machining	Good
Sapwood Lyctid susceptible	No

Stability	Excellent
Durability	Durable
Screwing Split Resistance	Fair
Nailing Split Resistance	Fair
Growing region	North America
Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

brittontimbers.com.au

