

# Cambia Maple

Acer Rubrum

The Cambia thermal modification process uses high heat to improve its dimensional stability and decay resistance giving it a rich brown colour. Cambia products are more dimensionally stable and less prone to cup, warp and twist. Cambia does not contain any toxic chemicals.

## Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating

Density	705	Hardness (janka) (kN)	6.0	Stability	Excellent
Specific Gravity	0.63	Finish	Excellent	Durability	Durable
Modulus of Rupture (Mpa Dry)	109	Gluing	Good	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	13	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	3%	Sapwood Lyctid susceptible	No	Growing region	North America
Tangential Shrinkage	6%			Availability	Widely

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
100 Potassium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Veneer Products  
(03) 6435 1108  
2 Elizabeth St  
Somerset TAS 7322

