

Cambia Poplar

Liriodendron Tulipifera

The Cambia thermal modification process uses high heat to improve its dimensional stability and decay resistance giving it a rich brown colour. Cambia products are more dimensionally stable and less prone to cup, warp and twist. Cambia does not contain any toxic chemicals.

Application Suitability

Decking & Cladding • Joinery

Density	449	Hardness (janka) (kN)	2.0	Stability	Excellent
Specific Gravity	0.42	Finish	Good	Durability	Durable
Modulus of Rupture (Mpa Dry)	69	Gluing	Poor	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	11	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	2.5%	Sapwood Lyctid susceptible	No	Growing region	North America
Tangential Shrinkage	6%			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170



brittontimbers.com.au

