


Celery Top Pine

Phyllocladus Asplenifolius, Phyllocladus Rhomboidalis

The heartwood colour is pale yellow, with clearly defined growth rings. It is straight grained, with a fine, even texture. No taste or odour. Also known as Celery Top, Tasmanian Celery Top Pine.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating



Density	650
Specific Gravity	0.64
Modulus of Rupture (Mpa Dry)	98
Modulus of Elasticity (Gpa Dry)	10
Radial Shrinkage	1.5%
Tangential Shrinkage	3.5%

Hardness (janka) (kN)	4.5
Finish	Excellent
Gluing	Good
Machining	Excellent
Sapwood Lyctid susceptible	No

Stability	Excellent
Durability	Durable
Screwing Split Resistance	Excellent
Nailing Split Resistance	Excellent
Growing region	Tasmania
Availability	Available

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322



brittontimbers.com.au

