

Damar Minyak

Agathis Dammara, Agathis Borneensis

Heartwood pale yellowish brown, sometimes with a pinkish tinge. Sapwood often hard to distinguish from the heartwood. Texture very fine and even. Grain straight. No figure. Free of brittleheart. Also known as East Indian Kauri, Indonesian Kauri.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Boating

Density	550	Hardness (janka) (kN)	3.0	Stability	Good
Specific Gravity	0.50	Finish	Excellent	Durability	Non Durable
Modulus of Rupture (Mpa Dry)	67	Gluing	Good	Screwing Split Resistance	Excellent
Modulus of Elasticity (Gpa Dry)	12	Machining	Excellent	Nailing Split Resistance	Excellent
Radial Shrinkage	1.5%	Sapwood Lyctid susceptible	No	Growing region	Asia Pacific
Tangential Shrinkage	3%			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170



brittontimbers.com.au

