

Durian

Durio, Neesia, Coelostegia Spp

Sapwood is only moderately well defined in Coelostegia but well defined in Durio and Neesia. Heartwood is pink brown, grey brown, brown with a red tinge or light orange brown. Grain is straight to slightly interlocked. Texture is moderately coarse and even in Neesia but uneven in Durio and Coelostegia.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring

Density	650	Hardness (janka) (kN)	6.0	Stability	Good
Specific Gravity	0.65	Finish	Good	Durability	Non Durable
Modulus of Rupture (Mpa Dry)	95	Gluing	Fair	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	16	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	2.5%	Sapwood Lyctid susceptible	Yes	Growing region	Asia Pacific
Tangential Shrinkage	4%			Availability	Available

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322

