

European Maple

Acer Pseudoplatanus

Heartwood creamy, darkening on exposure. Sapwood not clearly separated. Texture fine and even. Grain sometimes wavy, producing a fiddleback figure. Also known as Sycamore.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Boating

Density	610	Hardness (janka) (kN)	5.0	Stability	Good
Specific Gravity	0.61	Finish	Excellent	Durability	Non Durable
Modulus of Rupture (Mpa Dry)	99	Gluing	Excellent	Screwing Split Resistance	Excellent
Modulus of Elasticity (Gpa Dry)	10	Machining	Good	Nailing Split Resistance	Excellent
Radial Shrinkage	2%	Sapwood Lyctid susceptible	Yes	Growing region	Europe
Tangential Shrinkage	4%			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170



PEFC
PEFC/21-31-233



Australian Forestry Standard
AFS/01-31-233

brittontimbers.com.au

