

# Ironbark Grey

*Eucalyptus Paniculata*

Heartwood colour varies from pale brown to dark chocolate brown and also dark red. Texture moderately coarse and even. Grain usually interlocked.

## Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating

Density	1120	Hardness (janka) (kN)	14.0	Stability	Fair
Specific Gravity	1.10	BAL	29.0	Durability	Durable
Modulus of Rupture (Mpa Dry)	181	Finish	Fair	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	24	Gluing	Poor	Nailing Split Resistance	Fair
Radial Shrinkage	4.5%	Machining	Fair	Growing region	Australia
Tangential Shrinkage	8%	Sapwood Lyctid susceptible	No	Availability	Limited

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
100 Potassium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Veneer Products  
(03) 6435 1108  
2 Elizabeth St  
Somerset TAS 7322



[brittontimbers.com.au](http://brittontimbers.com.au)

