

Jarrah

Eucalyptus Marginata

Heartwood is a rich dark brownish red, sometimes marked by short, dark brown radial flecks on the end grain and boat shaped flecks on flat sawn surfaces which enhance it's decorative value. The grain is usually straight but often interlocked or wavy. The texture is even but moderately coarse. Also known as Western Australian Jarrah.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating



Density	820
Specific Gravity	0.80
Modulus of Rupture (Mpa Dry)	112
Modulus of Elasticity (Gpa Dry)	13
Radial Shrinkage	5%
Tangential Shrinkage	8%

Hardness (janka) (kN)	8.0
Finish	Good
Gluing	Good
Machining	Fair
Sapwood Lyctid susceptible	Yes

Stability	Good
Durability	Durable
Screwing Split Resistance	Fair
Nailing Split Resistance	Fair
Growing region	Australia
Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170