

Jelutong

Dyera Costulata

Heartwood is creamy white to straw coloured. The grain is almost straight, the texture fine and even and of plain appearance. Jelutong is mainly used for pattern making.

Application Suitability

Cabinetry • Joinery • Boating

| | | | | | |
|---------------------------------|------|----------------------------|-----------|---------------------------|--------------|
| Density | 400 | Hardness (janka) (kN) | 2.0 | Stability | Excellent |
| Specific Gravity | 0.46 | Finish | Excellent | Durability | Non Durable |
| Modulus of Rupture (Mpa Dry) | 50 | Gluing | Good | Screwing Split Resistance | Excellent |
| Modulus of Elasticity (Gpa Dry) | 8 | Machining | Excellent | Nailing Split Resistance | Excellent |
| Radial Shrinkage | 1% | Sapwood Lyctid susceptible | Yes | Growing region | Asia Pacific |
| Tangential Shrinkage | 2% | | | Availability | Available |

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322

