

Karri

Eucalyptus Diversicolor

Heartwood is reddish brown, paler in colour than Jarrah when fresh, but maturing to a more uniform brown. The grain is interlocked with some wavy grain, the texture is even and moderately coarse. Also known as Western Australian Karri.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating

Density	900
Specific Gravity	0.88
Modulus of Rupture (Mpa Dry)	132
Modulus of Elasticity (Gpa Dry)	19
Radial Shrinkage	4.5%
Tangential Shrinkage	10%

Hardness (janka) (kN)	9.0
Finish	Good
Gluing	Fair
Machining	Fair
Sapwood Lyctid susceptible	No

Stability	Good
Durability	Durable
Screwing Split Resistance	Fair
Nailing Split Resistance	Fair
Growing region	Australia
Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322

