

Karri

Eucalyptus Diversicolor

Heartwood is reddish brown, paler in colour than Jarrah when fresh, but maturing to a more uniform brown. The grain is interlocked with some wavy grain, the texture is even and moderately coarse. Also known as Western Australian Karri.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating

Density	900	Hardness (janka) (kN)	9.0	Stability	Good
Specific Gravity	0.88	Finish	Good	Durability	Durable
Modulus of Rupture (Mpa Dry)	132	Gluing	Fair	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	19	Machining	Fair	Nailing Split Resistance	Fair
Radial Shrinkage	4.5%	Sapwood Lyctid susceptible	No	Growing region	Australia
Tangential Shrinkage	10%			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170



brittontimbers.com.au

