

Northern Silky Oak

Branch 95

Heartwood is pale pink to pinkish-brown. Sapwood is usually almost white. Quarter sawn timber shows the decorative oak grain to best effect. The medullary rays that show in quarter sawn timber display the beauty for which this species is renowned.

Application Suitability

Furniture • Decking & Cladding • Joinery

Density	560	Hardness (janka) (kN)	6.0	Stability	Good
Modulus of Rupture (Mpa Dry)	66	Gluing	Good	Durability	4/4
Modulus of Elasticity (Gpa Dry)	9	Machining	Good	Screwing Split Resistance	Good
Radial Shrinkage	1.6	Sapwood Lyctid susceptible	Yes	Nailing Split Resistance	Good
Tangential Shrinkage	4.7			Growing region	QLD

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170



brittontimbers.com.au

