



Peninsula Ash

Peninsula Ash

Heartwood white to pale yellow-brown, darkening on exposure. Grain is shallowly interlocked and wavy. Texture medium and even. Lustrous, with faint ribbon figure on the quarter sawn face. Sapwood not well demarcated and white. Resin content present. Growth rings not apparent.

Application Suitability



Density	550
Specific Gravity	0.50
Modulus of Rupture (Mpa Dry)	81
Modulus of Elasticity (Gpa Dry)	10
Radial Shrinkage	1.5%
Tangential Shrinkage	2.5%

Hardness (janka) (kN)	3.2
Finish	Good
Gluing	Good
Machining	Poor
Sapwood Lyctid susceptible	Yes

Stability	Good
Durability	No
Screwing Split Resistance	Poor
Nailing Split Resistance	Poor
Growing region	Asia Pacific
Availability	Available

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
(03) 6435 1108
2 Elizabeth St
Somerset TAS 7322

