

# Queensland Maple

Branch 95

Heartwood is pink to brownish pink, tan- red, mid- brown, straw through to honey while the narrow sapwood band is coloured white to pale grey. The grain is somewhat interlocked, at times it exhibits, fiddle back and ripple caused by sudden dips in the growth rings.

## Application Suitability

Furniture • Decking & Cladding • Joinery • Boating

Density	575	Hardness (janka) (kN)	4.7	Stability	Good
Modulus of Rupture (Mpa Dry)	77	Gluing	Great	Screwing Split Resistance	Great
Modulus of Elasticity (Gpa Dry)	10	Machining	Good	Nailing Split Resistance	Great
Radial Shrinkage	0.15	Sapwood Lyctid susceptible	No	Growing region	QLD
Tangential Shrinkage	0.25				

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
100 Potassium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170



[brittontimbers.com.au](http://brittontimbers.com.au)

