

Queensland Silver Ash

Branch 95

Heartwood ranges from silver-white to pale yellow shades. There is no noticeable colour difference between sapwood and heartwood. The grain is open and predominantly straight.

Application Suitability

Flooring • Furniture • Joinery

Modulus of Rupture (Mpa Dry)	92	Hardness (janka) (kN)	5.0	Stability	Great
Modulus of Elasticity (Gpa Dry)	13	Gluing	Excellent	Screwing Split Resistance	Excellent
Radial Shrinkage	3.0	Machining	Excellent	Nailing Split Resistance	Excellent
Tangential Shrinkage	5.5	Sapwood Lyctid susceptible	Yes	Growing region	QLD

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

brittontimbers.com.au

