

Red Silkwood

Branch 95

Heartwood generally varies from pale pink to reddish brown or purple brown sometimes with darker streaks. The grain is straight to shallowly interlocked. The timber is reported to resemble Makore. The heartwood is moderately resistant to decay and could last between 10 to 15 years in contact with ground.

Application Suitability

Furniture • Joinery

Density	560	Hardness (janka) (kN)	5.0	Stability	Good
Modulus of Rupture (Mpa Dry)	77	Gluing	Satisfactory	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	10	Machining	Well	Nailing Split Resistance	Fair
Radial Shrinkage	0.15	Sapwood Lyctid susceptible	Yes	Growing region	QLD
Tangential Shrinkage	0.25				

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170



brittontimbers.com.au

