

Red Tulip Oak

Branch 95

Found in Nth Qld with a pink to red-brown heartwood and whitish sapwood. Grain is usually straight and open. Attractive 'water wave' figure on tangential face and large ray fleck on radial face are prominent features of the tulip oaks.

Application Suitability

Flooring • Furniture • Joinery

Density	800	Hardness (janka) (kN)	9.0	Stability	Good
Modulus of Rupture (Mpa Dry)	126	Gluing	Good	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	15	Machining	Difficult	Nailing Split Resistance	Fair
Radial Shrinkage	3.6	Sapwood Lyctid susceptible	Yes	Growing region	QLD
Tangential Shrinkage	8.6				

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170



brittontimbers.com.au

