


River Red Gum

Eucalyptus Camaldulensis, Eucalyptus Rostrata

The heartwood varies according to location in age, from pink to dark red. The grain is interlocked and frequently wavy which produces a fiddleback figure when quarter cut. The texture is close and even. The wood is resinous with frequent gum pockets. The surface is often distinctly mottled. Also known as Murray Red Gum.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding



Density	900
Specific Gravity	0.90
Modulus of Rupture (Mpa Dry)	101
Modulus of Elasticity (Gpa Dry)	11
Radial Shrinkage	2.5%
Tangential Shrinkage	4%

Hardness (janka) (kN)	10.0
BAL	29.0
Finish	Good
Gluing	Fair
Machining	Fair
Sapwood Lyctid susceptible	Yes

Stability	Good
Durability	Durable
Screwing Split Resistance	Fair
Nailing Split Resistance	Fair
Growing region	Australia
Availability	Available

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170