

# Rose Gum

*Eucalyptus Grandis*

Heartwood pink to pale red brown. Sapwood not always clearly differentiated. Texture moderately coarse but even. Grain straight. Also known as Flooded Gum.

## Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating

|                                 |      |                            |      |                           |           |
|---------------------------------|------|----------------------------|------|---------------------------|-----------|
| Density                         | 700  | Hardness (janka) (kN)      | 8.0  | Stability                 | Good      |
| Specific Gravity                | 0.70 | Finish                     | Good | Durability                | Durable   |
| Modulus of Rupture (Mpa Dry)    | 122  | Gluing                     | Good | Screwing Split Resistance | Good      |
| Modulus of Elasticity (Gpa Dry) | 17   | Machining                  | Good | Nailing Split Resistance  | Good      |
| Radial Shrinkage                | 4%   | Sapwood Lyctid susceptible | No   | Growing region            | Australia |
| Tangential Shrinkage            | 7%   |                            |      | Availability              | Available |

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
29 Sodium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170



PEFC  
PEFD21-31-233



Australian  
FORESTRY  
STANDARD  
AFS/01-31-233

[brittontimbers.com.au](http://brittontimbers.com.au)

 **BRITTON  
TIMBERS**