

# Rosewood

**Pterocarpus Indicus**

Heartwood can be either golden brown or a dark blood red. Sapwood pale yellow. Texture medium. Grain variable. The freshly cut wood has a fragrant odour often highly figured. Also known as New Guinea Rosewood, Solomon Islands Rosewood.

## Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating

Density	650	Hardness (janka) (kN)	5.0	Stability	Excellent
Specific Gravity	0.65	Finish	Excellent	Durability	Durable
Modulus of Rupture (Mpa Dry)	95	Gluing	Good	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	12	Machining	Excellent	Nailing Split Resistance	Good
Radial Shrinkage	1%	Sapwood Lyctid susceptible	No	Growing region	Asia Pacific
Tangential Shrinkage	2%			Availability	Available

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
29 Sodium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170



[brittontimbers.com.au](http://brittontimbers.com.au)

