

Silver Quandong

Branch 95

Heartwood is generally white to cream-white, but may have greyish or light brownish tones. Sapwood and heartwood have no noticeable colour difference. Porous and open grain, Characteristic long, straight vessel lines on dressed longitudinal surfaces, but no obvious figure (pattern).

Application Suitability

Furniture • Joinery • Boating • Decking & Cladding

Density	495	Hardness (janka) (kN)	5	Stability	Good
Modulus of Rupture (Mpa Dry)	126	Gluing	Satisfactory	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	15	Machining	Well	Nailing Split Resistance	Fair
Radial Shrinkage	4	Sapwood Lyctid susceptible	Yes	Growing region	QLD
Tangential Shrinkage	4				

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170



brittontimbers.com.au

