

# Surian

Cedrela Calantas

Heartwood reddish brown. Sapwood narrow, pale red and distinctive. Texture moderately coarse. Grain often interlocked. Characteristic cedar odour. The wood is very similar to that of Australian red cedar. Also known as Kalantas, Red Cedar.

## Application Suitability

Joinery

Density	480	Hardness (janka) (kN)	2.0	Stability	Good
Specific Gravity	0.45	Finish	Excellent	Durability	Durable
Modulus of Rupture (Mpa Dry)	65	Gluing	Fair	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	8	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	4%	Sapwood Lyctid susceptible	Yes	Growing region	Asia Pacific
Tangential Shrinkage	7%			Availability	Available

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jedda Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
29 Sodium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jedda Road  
Prestons, NSW 2170



[brittontimbers.com.au](http://brittontimbers.com.au)

