

Wenge

Millettia Laurentii

The clearly defined heartwood is dark brown, with very close, fine, almost black veins. The closely spaced whitish bands parenchyma give the wood a most attractive appearance. It is fairly straight grained with a coarse texture.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Boating

Density	910	Hardness (janka) (kN)	10.0	Stability	Good
Specific Gravity	0.74	Finish	Good	Durability	Durable
Modulus of Rupture (Mpa Dry)	152	Gluing	Fair	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	16	Machining	Good	Nailing Split Resistance	Fair
Radial Shrinkage	3%	Sapwood Lyctid susceptible	No	Growing region	Africa
Tangential Shrinkage	6%			Availability	Available

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jedda Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
29 Sodium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jedda Road
Prestons, NSW 2170



brittontimbers.com.au

